



# 1318 Tape

## Polyester Film Tape with Acrylic Pressure-Sensitive Adhesive

### Data Sheet

#### Product Description

3M™ 1318 Tape is a polyester film tape with acrylic pressure-sensitive adhesive. It has excellent flagging resistance and solvent resistance, making it well suited for applications where cleaning solvents and mineral oil are present. It consists of materials that are represented in many UL Recognized Insulation Systems and has a UL 130°C temperature rating. It offers good wet grab, excellent shelf life, smooth, even unwind and is suitable for printing and use on automated equipment.

- UL Recognized Class 130°C
- Excellent flagging resistant
- Printable
- Solvent resistant without thermosetting
- Excellent shelf life

#### Applications

3M 1318 Tape is especially suited for applications such as wrapping coils, capacitors, wire harnesses, transformers, shaded pole motors and fractional horsepower motors.

#### Colors

3M 1318 Tape is available in yellow, white and black.

#### UL Component Recognition

UL recognized for use at temperatures not exceeding 130°C. UL File Number E17385, Guide OANZ2. Underwriters Laboratories (UL) recognized products are evaluated for use as components of end-product equipment that is listed or classified by UL. To achieve Underwriters Laboratories recognition, component construction must meet UL specifications and conditions of acceptability for proper and safe use of the component or products.

Typical Properties	1 Mil Film	2 Mil Film
Adhesive	Acrylic	Acrylic
Backing	Polyester Film	Polyester Film
Backing Thickness <sup>1</sup>	One mil (25 micron)	Two mils (50 micron)
Total Thickness	2.5 mils / 0,063 mm	3.3mils / 0,083 mm
Colors - Designation	Y, W, Blk	Y, W, Blk
Temperature Class	130°C/266°F	130°C/266°F
Dielectric Breakdown <sup>1</sup>	5,500 Volts	7,000 Volts
Insulation Resistance <sup>1</sup> (megohms)	>1 x 10 <sup>6</sup>	>1 x 10 <sup>6</sup>
Breaking Strength <sup>1</sup>	25 lbs./in (44N/10mm)	50 lbs./in (88N/10mm)
Elongation <sup>1</sup> (% at break)	100	110
Electrolytic Corrosion Factor <sup>2</sup>	1.0	1.0
Adhesion to Steel <sup>1</sup>	30 oz/in (3,3N/10mm)	30 oz/in (3,3N/10mm)
Printable	Yes	Yes
CTI Material Group	I	I

**Note: Typical properties are not recommended for specification purposes. Product specifications will be provided upon request.**

\*Footnote:

<sup>1</sup>Test method ASTM D 1000

<sup>3</sup>M Test Method-Available on request.

#### Important Notice

Technical information provided by 3M is based on experience and/or tests believed to be reliable, but their accuracy is not guaranteed and the results may not be relevant to every user's application. For this reason 3M does not accept responsibility or liability, direct or consequential, arising from reliance upon any information provided and the user should determine the suitability of the products for their intended use. Nothing in this statement will be deemed to exclude or restrict 3M's liability for death or personal injury arising from its negligence. All questions of liability relating to 3M products are governed by the seller's terms of sale subject where applicable to the prevailing law

If any goods supplied or processed by or on behalf of 3M prove on inspection to be defective in material or workmanship, 3M will (at its option) replace the same or refund to the Buyer the price paid for the goods or services. Except as set out above, all warranties and conditions, whether express or implied, statutory or otherwise are excluded to the fullest extent permissible at law.

3M and Scotchcast are trademarks of the 3M Company. Printed in the UK.

© 3M United Kingdom PLC, 1999

**3M United Kingdom PLC**  
**Electrical Products Group**  
**Hudson Road**  
**Bedford MK41 0HR**  
**Tel: 01234 268868**  
**Fax: 01234 229433**

**3M Ireland**  
**Electrical products Group**  
**3M House, Adelphi Centre**  
**Dun Loaghaire, CO. Dublin, Ireland**  
**Tel: (01) 2803555**  
**Fax: (01) 2803509**

**3M Innovation**

Jan. 2000