

3M™ CeQUIN 30F30 3-1-3 Laminate

Triplex Electrical Insulating Paper

Data Sheet

July 2010

CeQUIN 30F30 is CeQUIN 3000 inorganic based insulating paper bonded to both sides of polyester (PET) film. CeQUIN 30F30 is qualified for use as major ground insulation in electrical insulation systems rated through Class 220(R) per UL 1446 and IEC Std. 61857. It is suitable for applications including ground and layer insulation in dry-type transformers, as well as spiral-wound tubing and interwinding insulation in strip-wound coils and electromagnet coils. 3M Innovative Paper Technologies UL Recognized Insulation Systems (File No. 65007) may be found on UL's Electrical Insulation Systems Database at <http://www.ul.com/eis/>.

		ASTM Test Method	30F30 3-1-3
Nominal Thickness	mm mil	D-645	0.18 7
Basis Weight	g/m ² lb/yd ²	D-202	195 0.36
Density	g/cc		1.3
Tensile Strength, MD	lb/inch N/cm	D-828	35 61
Tensile Strength, CD	lb/inch N/cm	D-828	25 44
Elmendorf Tear, MD	g N	D-689	115 1.13
Elmendorf Tear, CD	g N	D-689	160 1.60
Dielectric Breakdown Strength	kV	D-149	6
Moisture Absorption	%	D-644	<1

Important Notice

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product, which are not contained in 3M's current publications, or any contrary statements contained on your purchase order, shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.

Warranty; Limited Remedy; Limited Liability

This product will be free from defects in material and manufacture at the time of purchase. 3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. Except where prohibited by law, 3M will not be liable for any indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.

3M is a trademark of 3M Company.

Electrical Markets Division 3M Innovative Paper Technologies

1 Paper Trail
Tilton, NH 03276-5250
866 357 2737
FAX: 603 286 4859
www.3M.com/flexibleinsulation

Please recycle
© 3M 2010 All rights reserved
xx-xxxx-xxxx-x A

