



# 180

Irradiation Cross-Linked Polymeric Insulation

UL 3740 180°C 600V  
CSA AWM 1 A/B 180°C 600V  
ROHS and CE Compliant

Exar® 180 the first Class H, 600 volt, irradiated cross-linked wire. Exar 180 is lower cost, thin insulated hook-up wire. Why pay the higher cost of a fluoropolymer or braided silicone insulated wire? EXAR 180 can cost effectively replace Teflon's and other fluoropolymer insulations. Irradiation cross-linking assures this insulation will not melt or flow at higher temperatures. It has excellent mechanical strength, cut through resistance and outstanding chemical and solvent resistance. Unlike most Teflon insulated wire, EXAR 180 is easier to print and pot.



Product Number	Standard Conductors Tinned Copper	Nom. Dia of Conductor		Insulation Thickness		Nom. OD		Finished Weight (lbs/mft)	Ampacity
		in.	mm.	in.	mm.	in.	mm.		
180-28/XX-B0	28 (7/36)	.015	.38	.016	.41	.049	1.25	1.40	1
180-26/XX-B0	26 (7/34)	.019	.48	.016	.41	.051	1.30	1.80	4
180-26/XX-E0	26 (19/38)	.020	.51	.016	.41	.053	1.35	1.87	4
180-24/XX-B0	24 (7/32)	.024	.61	.016	.41	.056	1.42	2.43	8
180-24/XX-E0	24 (19/36)	.024	.61	.016	.41	.057	1.45	2.48	8
180-22/XX-B0	22 (7/30)	.030	.76	.016	.41	.062	1.58	3.40	15
180-22/XX-E0	22 (19/34)	.031	.79	.016	.41	.063	1.60	3.51	15
180-20/XX-B0	20 (7/28)	.038	.97	.016	.41	.070	1.78	4.89	19
180-20/XX-E0	20 (19/32)	.038	.97	.016	.41	.071	1.80	5.10	19
180-18/XX-B0	18 (7/0152)	.045	1.14	.016	.41	.077	1.96	6.55	26
180-18/XX-D0	18 (19/0092)	.045	1.14	.016	.41	.077	1.96	6.45	26
180-16/XX-F0	16 (19/0117)	.058	1.47	.016	.41	.092	2.34	9.99	33
180-14/XX-H0	14 (41/30)	.071	1.85	.016	.41	.107	2.72	15.07	50
180-12/XX-J0	12 (65/30)	.089	2.26	.016	.41	.121	3.07	23.08	64
180-10/XX-J0	10 (65/28)	.111	2.81	.017	.43	.145	3.68	34.25	85
180-08/XX-X0	8 (84/27)	.147	3.73	.024	.61	.195	4.95	64.15	115
180-06/XX-X0	6 (84/25)	.183	4.65	.024	.61	.231	5.87	97.46	160
180-04/XX-L0	4 (133/25)	.263	6.68	.024	.61	.311	7.90	150.00	205
180-02/XX-M0	2 (259/26)	.323	8.20	.024	.61	.371	9.42	231.00	274
180-01/XX-M0	1 (259/25)	.372	9.44	.030	.76	.432	10.97	295.00	319



Manufacturing Locations:  
Colchester, Vermont  
El Paso, Texas  
Leeds, Massachusetts



Irradiation Cross-Linked Polymeric Insulation

# 180

PROPERTIES	EXAR® 180
<b>Approvals / Listings:</b>	
UL	UL STYLE 3740
CSA	AWM 1 A/B
<b>Physical Properties: *</b>	
Temperature Rating (UL 3740)	1850°C
Voltage Rating (Vrms)	600V
Scrape Abrasion Resistance	818 cycles
Shore "A" Hardness	NA
Shore "D" Hardness	80
Cold Bend - 4h @ -70°C	Passes
Bend Radius	5- 9 Overall Diameter
<b>Tensile Strength: *</b>	
Unaged	6,050 psi
Retention after 7 days @ 210°C	Pass (> 85%)
<b>Elongation: *</b>	
Unaged	410%
Retention after 7 days @ 210°C	Pass (> 110%)
<b>Flame Test: *</b>	
VW-1 FT1	Passes
<b>Oil Resistance 135°C maximum.</b>	
1500 hrs. @150°C	Tensile -16% Elongation -57%
<b>Chemical Resistance</b>	
Acetone	swell@23°C** 0%
Acid - H2SO4 S.G. 1.260 5%	swell@23°C** 0%
Engine Oil – ASTM D-471 IRM-902	swell@50°C** 0%
Benzene	swell@23°C/24h 0%
Epoxy	swell@23°C/24h <1%
Gasoline – ASTM D-471 Fuel C	swell@23°C** 0%
Methanol	swell@23°C/24h 0%
Toluene	swell@23°C/24h 0%
Xylene	swell@23°C/24h 0%
<b>Electrical: *</b>	
Dielectric Constant	7.4
Dielectric Breakdown Strength (Vrms)	19,000
<b>Oxygen Index:</b>	42

We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product combination for their own purpose. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss and damage arising from the handling and use of our products whether used alone or in combination with other products



## Sales Offices:

