

**Technical Data Sheet** 

**Secondary Insulation** 



**Air-Drying Impregnating Resin** 

ELANTAS PDG, Inc.

5200 North Second Street St. Louis, MO 63147 USA Tel +1 314 621-5700 Fax +1 314 436-1030 info.elantas.pdg@altana.com www.elantas.com



# RanVar<sup>™</sup> B277

### **Product Description**

RanVar<sup>™</sup> B277 is a clear, air-drying, modified alkyd impregnating resin.

### **Areas of Application**

Impregnation of motor stators, transformers and coils

Insulating dip coating of coils and electronic components

### **Features and Benefits**

- Fast drying
- Excellent moisture resistance
- Thermal ratings to Class 180

#### **Application Methods**

• Dip-and-Bake

### **Transportation / Storage**

Store below 25°C / 77°F in a dry controlled environment out of direct sunlight. This material should be suitable for use stored under these conditions in the original sealed containers for twelve (12) months from the date of shipment.

Failure to store the product as recommended above may lead to deterioration in product performance.

Keep containers tightly sealed to minimize evaporation.

Mix product thoroughly before use

### Health / Safety

Refer to the Material Safety Data Sheet.

<b>Typical Properties of Material as</b>	Supplied
--	----------

Property	Conditions	Value	Units
Viscosity	25°C / 77°F	400 - 800	cP
% Non-Volatiles	1.5 g - 3 h - 110°C	49 - 51	%
Weight per Gallon	25°C / 77°F	7.65 - 7.95	pounds
Flash Point	ASTM D93	26 °C 79 °F	
Adjustment thinner		ELAN-Plus™ BS-107 Reducer	



# RanVar<sup>™</sup> B277

# **Curing Schedule**

RanVar<sup>™</sup> B277 will air dry at 25°C / 77°F to a tack-free surface in 15 - 30 minutes and a hard surface in 1 - 2 hours. Cure can be accelerated by baking at 110°C / 230°F for 30 minutes after an initial flash-off of one minute.

Impregnated windings must allow a minimum of three days at room temperature for evaporation of solvent and penetration of oxygen to achieve best properties.

### **Typical Electrical Properties**

### Specimens cured 72 hours at 25°C / 77°F

Property	Conditions	Value	Units
Dielectric Strength	ASTM D149 - 2 mils	2200	volts/mil
Dielectric Strength	ASTM D149 - 2 mils After 24 hours in water	1800	volts/mil

# **Underwriters Laboratories Recognition (ELANTAS File E75225)**

Wire Construction	Helical Coil	Twisted Pair
NEMA MW24	130	155
NEMA MW26	155	155
NEMA MW28	105	130
NEMA MW30	180	180
NEMA MW35	130	180

# UL Recognized Insulation Systems (ELANTAS File E87039)

Thermal Class	System
Class 130	MEGA I
Class 155	B2
Class 180	MEGA III

The above properties are typical values and are not intended for specification use.

ELANTAS PDG, Inc. warrants the chemical composition of its products within stated tolerances, but does not guarantee that a product will be appropriate for any particular application. Any recommendation, performance of tests or suggestion is offered merely as a guide and is not a substitute for a thorough evaluation by the user. No representative of ELANTAS PDG, Inc. has the authority to offer a warranty that a product will perform satisfactorily in manufacturing a product and no such representation should be relied upon.