



Grade TSF 1312


General-Purpose Laminate

- NEMA GPO-1
- Extremely Cost-Effective
- Outstanding Punchability
- Ideal For A Variety Of Applications
- UL® Recognized
- Easily Fabricated
- Asbestos-Free

Grade TSF 1312 General-Purpose Laminate is the most cost-effective fiberglass-reinforced laminate sheet available from Röchling Glastic Composites. It is also a NEMA GPO-1 Laminate and UL Recognized.

Grade TSF 1312 has a UL temperature index of 130° C Electrical and 130° C Mechanical. It is available in the color brown, in thicknesses of $\frac{1}{32}$ of an inch through $1\frac{1}{4}$ inches.

Grade TSF 1312 exhibits outstanding punchability in thin thicknesses. It is widely used in motors and dry-type transformers, as well as a variety of other applications.






Grade TSF 1312

	UNIT	ASTM/UL Number	Grade TSF
General Information			
Part Number			1312
Standard Color			Brown
Mechanical Properties			
NEMA Grade Li 1-1989			GPO-1/GPO-1P
Tensile Strength	Psi	D638	9,400
Tensile Modulus	Psi X 10 ⁶	D638	1.7
Flexural Strength	Psi	D790	22,300
Flexural Strength – 130°C	Psi	D790	15,400
Compressive Strength	Psi	D695	38,900
Shear Strength	Psi	D732	13,400
IZOD Impact Strength (notched)	ft. lb./in.	D256	8
Water Absorption	% by wt.	D570	0.3
Specific Gravity	–	D792	1.78
Electrical Properties			
Electrical Strength – Perpendicular S/T in Air	Vpm	D149	417
Electrical Strength – Perpendicular S/T in Oil	Vpm	D149	493
Electrical Strength – Parallel S/S in Oil	kV	D149	44
Arc Resistance	Sec.	D495	127
Permittivity, 60 Hz	–	D150	4.2
Dissipation Factor, 60 Hz	–	D150	0.0095
Permittivity, MHz	–	D150	4.2
Dissipation Factor, MHz	–	D150	0.010
Insulation Resistance	Ohm x 10 ¹²	D257	2.4
Flame Resistance Properties			
UL Subject 94	–	UL94	HB
Oxygen Index	%O ₂	D2863	21.8
Thermal Properties			
Coefficient of Thermal Expansion	In/In/°C x 10 ⁻⁵	D696	2.2
Thermal Conductivity	BTU/HR/Ft ² /In/°F	C177	1.8
UL Temperature Index			
– Electrical	°C	UL 746B	130
– Mechanical	°C	UL 746B	130
UL Recognition File Number	–	–	E23525

Typical average values for testing 0.063" thick material. Values will vary somewhat from thickness to thickness within a material grade.



Röchling Glastic Composites
 4321 Glenridge Road
 Cleveland, OH 44121 USA
 Tel: 216-486-0100
 Fax: 216-486-1091
www.glastic.com

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Röchling Glastic Composites products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Under no circumstances shall we be liable for incidental or consequential loss or damage.

Glastic® is a registered trademark of Röchling Glastic Composites. UL® is a registered trademark of Underwriters Laboratories, Inc.

©2013 Röchling Glastic Composites. All Rights Reserved. Printed in USA.